



Surf

Specifications

Contents

100% FR polyester

Weight

13.4 ± 1.0 oz./lin. yd.

Width

72" min. useable

Repeat

35" vertical, 37.7" horizontal

Treatment

Antimicrobial

Backing

none

Treatment

Antimicrobial

Performance



Breaking Strength (ASTM D5034)

225 lbf min. warp and 100 lbf min. fill

Tear (ASTM D2261)

10 lbf min. warp and fill

Seam Slippage (ASTM D4034)

60 lbf min. warp and fill

Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 60 hours

Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

Flammability

CA Technical Bulletin 117-2013 Section 1