



Meets or exceeds all ACT® Standards

High Performance Vinyl Bleach Cleanable FR Free – Compliant with CAL AB 2998

₩★□.

*ACT® Registered Certification Marks



Fabric Specifications		
Face	100% Vinyf	
Backing	100% Polyester	
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution	
Weight	28.0 oz. per linear yd	
Thickness	1.00 mm	
Width	54"	
Roll Size	30 yards	

Yes

No

Please refer to Detailed Cleaning Instructions.

Additional Attributes

Directional

Railroaded

Resilience*	Yes
Free of Added Anti-Bacterial Chemicals	Yes
Free of Added Anti-Microbial Chemicals	Yes
BPA Free	Yes
Formaldehyde Free	Yes
Free of Added FR Chemicals / CAL A82998 Compliant	Yes
Free of Conflict Minerals	Yes
Free of Heavy Metals	Yes
Lead Free	Yes
Mildew Resistant	Yes
16P Phthalate Free	Yes
Sulfide Stain Resistant	Yes
TRIS Free	Yes
Recommended Cleaning	

Performance Characteristics			
Abrasion Resistance ASTM 04157	250,000 double rubs*		
Tensile Strength CFFA-17	Warp: 95.0 lbs.		
	Fill: 60.0 lbs.		
Tear Strength CFFA-16	Warp: 5.1 lbs.		
	Fill: 6.9 lbs.		
Seam Slippage CFFA-14	Warp: 45.0 lbs		
	Fill: 45.0 lbs.		
Colorfastness to Crocking AATCC 8	Dry: 5.0		
	Wet: 5.0		
UV Resistance office	650 hours		
Adhesion CFFA-3	Warp: 6.3 lbs.		
	Fill: 5.6 lbs.		
Blocking CFFA-4	2		
Cold Crack CIFA-6	-20" F		
Flex CFFA-10	25,000 cycles		
Flammability**			
CAL TB 117-2013	Passes		
NFPA 260	Class 1		
JFAC	Class 1		
BIFMA CS-191-53, Sec. 3	Passes		
BIFMA Upholstery, Sec. 4	Passes		
MO 2010 FTP Part 8, 3.1 & 3.2	Passes		
MVSS 302	Passes		

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

- Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.
- ** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.